



Cempolay Ultra Strong

A STRONG, FAST SETTING RESURFACING & SMOOTHING COMPOUND

Date: 16 April 2021

Fact Sheet No.: TDS00001

YOUR SMART ADVANTAGES

- Water and frost resistant once cured
- Suitable for use as a final wear layer when over painted
- Interior and exterior use

USES

Bostik Cempolay Ultra Strong is strong, fast setting, protein-free, resurfacing & smoothing compound for levelling interior subfloors prior to laying decorative floor coverings, or painting. It is also suitable for some exterior applications, prior to laying ceramic tiles, slabs & natural stone, and can also be used on domestic garage floors prior to over coating with a suitable floor paint.

It is ideal for smoothing and levelling prepared concrete subfloors, sand/cement screeds and unglazed ceramic tiles. It can be extended for filling holes and forming sloping screeds (5% downward gradients).

It is suitable for use with warm water underfloor heating systems, provided a surface temperature of +27°C is not exceeded. It is not suitable for use on tarmac, vinyl, or floors prone to structural movement.

PRODUCT CHARACTERISTICS

Colour	Grey
Form	Dry, free-flowing powder
Specific Gravity	1.6 approx.
Composition	Blend of cement and fillers
Product Codes	30812526 25kg bag
Storage/Shelf Life	Store and transport securely. Store for up to 6 months from date of manufacture in original, unopened packaging, clear of the ground, in cool, dry conditions within the

temperature range +5°C to +25°C and out of direct sunlight. Protect from excessive drafts, frost, damp, condensation and dew.

TYPICAL PERFORMANCE DATA (Approx.)

Application Temperature	+5°C to +25°C
Coverage	Approx. 7.3m ² per bag at 2mm depth Approx. 5m ² per bag at 3mm depth Approx. 3m ² per bag at 5mm depth Approx. 0.75m ² per bag at 20mm depth (depending on the smoothness of the floor surface & application technique)
Gauging Liquid	Water
Application Thickness	2mm to 20mm
Working Times	15 to 20 minutes after mixing (depending on ambient temperatures)
Drying Times	Foot traffic: approx. 2 to 3 hours at +20°C Ceramic tiles: approx. 3 hours at +20°C Impervious floor coverings: approx. 24 hours per 10mm depth at +20°C
Cleaning	Clean tools and equipment with warm, soapy water immediately after use

DIRECTIONS FOR USE

IMPORTANT: Before using Bostik Cempolay Ultra Strong, refer to the relevant Health & Safety Data Sheet, available at www.bostik.com/uk.

All phases of installation should comply with the latest editions of:

- BS 8102 Code of Practice for protection of structures against water from the ground.
- BS 5325 Code of Practice for installation of textile floor coverings.
- BS 8203 Code of Practice for installation of resilient floor coverings.
- BS 8201 Code of Practice for installations of for flooring of timber, timber products and wood based panel products.

PREPARATION

Subfloor:

1. Ensure the subfloor is sound, clean, dry and of adequate tensile and compressive strength, free from loose material, laitance, cracks and structural defects. Ensure there is an effective damp-proof membrane, which conforms to BS 8203.
2. The subfloor should be tested in accordance with British Standards, using a properly calibrated and insulated hygrometer. A reading of 75% RH or less confirms that the subfloor is satisfactorily dry.
3. Any contaminants that may hinder adhesion, such as grease, oil, dirt, dust, plaster, some curing compounds, surface hardeners, additives and adhesive residues must be completely removed. Bostik Cempolay Ultra Strong does not tolerate any contamination.
4. Any cracks or holes in the floor must be cleaned out and filled with Bostik Rapid Repair Mortar. Allow to dry before applying Bostik Cempolay Ultra Strong.
5. For optimum performance, a room temperature of +13°C to +18°C should be maintained for at least 24 hours prior to application. The temperature of the subfloor must be at least +5°C throughout the application and drying of the smoothing compound. Ensure that a maximum room temperature of +25°C is not exceeded during application. Do not apply externally if temperatures are likely to drop below freezing within 7 days of application. The temperature must remain above +5°C.

Underfloor heating systems:

6. Warm water underfloor heating systems must be switched off for 48 hours before installation. Wait 48 hours after installation before gradually turning up underfloor heating.

PRIMING

7. Prime porous surfaces with Bostik SBR diluted with 4 parts water. Allow to dry before applying Bostik Cempolay Ultra Strong.
8. Prime non-porous surfaces/unglazed ceramic tiles with undiluted Bostik SBR, and apply Bostik Cempolay Ultra Strong while it is still tacky, usually about 30 minutes. If it has dried, apply a further coat of Bostik SBR.

MIX RATIOS

Smoothing compound:

- 5 litres of water to 25kg Bostik Cempolay Ultra Strong.

Bulked out compound:

- 4 litres of water to 25kg Bostik Cempolay Ultra Strong + 12.5kg of dry, sharp sand (0mm to 4mm).
- Or, 4 litres of water to 25kg Bostik Cempolay Ultra Strong + 12.5kg of granite chippings (3mm).

MIXING & APPLICATION DEPTH

9. According to the mix ratios above, pour clean, cold water into a clean mixing bucket. Gradually add Bostik Cempolay Ultra Strong powder to the water, whilst continually mixing with an electric drill and mixing paddle until a smooth, lump-free mixture is obtained.
10. Do not mix more compound than you can use in 15 to 20 minutes. The mixture will remain workable for approximately 20 minutes under normal conditions. If the mix begins to stiffen before it has been spread, it must be discarded. Do not re-temper, or add further water.

Note: the addition of too much water may result in separation of the compound.

11. Bostik Cempolay Ultra Strong can be applied from a minimum depth of 2mm, up to 20mm in a single application. However, when applying at depths greater than 10mm it may be beneficial to bulk out the compound with dry, sharp sand or granite chippings.

Bulked out compound:

12. The sand or chippings must be dry and added after mixing the water and powder together. Use the mix ratios and mixing process detailed above.

NOTE: Bulked out compound is not suitable for use with underfloor heating systems.

APPLICATION

13. Pour the mixed material onto the prepared subfloor in a continuous operation and allow to flow.
14. Using a steel screeding trowel, spread evenly to the required depth and smoothness.
15. Protect surface from foot traffic prior to laying a floor covering. Ensure the compound is fully dry before applying a floor covering.

DRYING TIMES

16. Protect freshly applied product from strong sunlight and through draughts, as this can dehydrate the product, resulting in incorrect curing. Also, protect from rain and frost. Do not force dry the smoothing compound, as this may affect the curing process.
17. Application in high temperatures may result in rapid setting and poor flow. The rapid loss of water may increase the risk of cracking.
18. The drying time depends on how absorbent the

subfloor is, the air humidity and both the ambient & floor temperatures.

19. Under good site conditions, Bostik Cempolay Ultra Strong will normally take foot traffic 2 to 3 hours after application. Leave overnight before applying impervious floor coverings, or 24 hours for every 10mm. Ceramic tiles may be laid in as little as 3 hours, when a cement-based adhesive is used. The walk on time and setting time will be delayed if the powder has been stored in temperatures below +10°C, or has been applied in temperatures below +20°C.
20. The working and drying times of the compound will be reduced in higher temperatures and increased in lower temperatures.

FINISHING

21. If Bostik Cempolay Ultra Strong is to be left exposed as a wearing surface on domestic garage floors, apply a suitable transparent varnish or paint to protect the compound. Externally, Bostik Cempolay Ultra Strong must be covered by ceramic tiles, slabs or natural stone.

CLEANING

22. Clean tools and equipment with warm, soapy water immediately after use. Remove surplus compound from surfaces whilst it is still wet. Cured material can only be removed mechanically.

PRECAUTIONS IN USE

Do not use as a substitute for a DPM. An effective membrane is required to prevent water entering the system.

The mix ratios and temperatures need to be followed accurately. Changing the mix ratios will disrupt the system and risk product failure.

For any application not covered, please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.com/uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data sheet for Bostik Cempolay Ultra Strong, available at www.bostik.com/uk.

BOSTIK HOTLINE

Smart help +44 (0) 1785 272625



**CONSTRUCTION PRODUCT REGULATION
DECLARATION OF PERFORMANCE**

No: TDS00001

Product Description: **Bostik Cempolay Ultra Strong**
Product Code: **5010591366008**
Intended Use: **Cementitious screed material**
Manufacturer:
Contact Address: **Bostik Ltd
Common Road
Stafford
ST16 3EH**
System of Assessment: **System 4**
Harmonised Standard: **EN 13813:2002**
Declared Performance: **CT-C20-F6**

Essential characteristics	Performance	Harmonised technical specification
Compressive strength	$\geq 20\text{N/mm}^2$	EN 13813:2002
Flexural strength	$\geq 6\text{N/mm}^2$	
Reaction to fire	F	

The performance of the product Bostik Cempolay Ultra Strong 5010591366008 is in conformity with the declared performance shown in the table above.

This declaration of performance is issued under the sole responsibility of Bostik Ltd.

Signed for and on behalf of Bostik Ltd by:

Name: Marrienne Drayton

Function: Quality Manager

Signature:



Date: January 2021

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Sales	Tel: 0844 371 1192	Fax: 01785 241818	customer.service@bostik.com
Technical Advice	Tel: 0844 371 1197	Fax: 01785 272867	technical.service@bostik.com
Safety Data Sheets	Tel: 01785 272625	Fax: 01785 212962	sds.box-eu@bostik.com